



Bull





Bull

Meet Bull, a perfect fit for our Textaafoam Skins Collection. This collection contains all kinds of best leather looking qualities.

The unique characteristic of this article is the 'leather aspect' together with the pleasant handfeel of fabric.

The backing of Bull exists out of 100% recycled leather fibres. Leather leftovers are ground by a shredder and after a special process flocked on a knitted microfiber. This unique leather fibre backing creates this special, comfortable and thick grip.

The top layer is a knitted microsuede with a leather print and an embossing. Bull has also been finished with a damp and dirt prevented treatment.

Through daily use this 'used aspect' will become more visible, this has no further influence on the quality or durability of this fabric.

- Dirt and damp prevention treatment applied.

***Textaafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 96%PES 4%PU
/ backside 100%LEATHER FIBRES
/ microsuede knitted

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



almond 82



anthracite 67



beige 05



brandy 127




brown 15



camel 09



caramel 16



clay 84



cognac 28



darkblue 48



darkbrown 18




desert 109

Please note: colours may vary according to your screen settings.



eucalyptus 193



forest 162




graphite 66



grey 65



hunter 156



lightgrey 60



liver 10




magnolia 160



moss 59



natural 01



niagara 158




onyx 169

Please note: colours may vary according to your screen settings.



shell 196 (new colour)



steel 149



thyme 206



tobacco 111



winered 39



wood 108

Please note: colours may vary according to your screen settings.

Bull - Article passport

The unique characteristic of this article is the 'leather aspect' together with the pleasant handfeel of fabric.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	microsuede knitted
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	96%PES 4%PU
Composition backside	100%LEATHER FIBRES
Bonding	flocked leather fibres
Statistic code	590700090
Dyeing method	piece dyed
Available colours	30
Packaging	boxes

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	32.000		min. 8.000	min. 16.000	C
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	3-4		min. 3-4	min. 4	C
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	3-4		min. 4	min.5	C
	middle colours	CTL	grade	3-4		min. 4	min.5	C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 138
Roll length in meters	± 35
Material weight in grams per linear meter	± 672

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.088	825	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	73,7	54,1	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	1,5	1,5	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	13,1	13,9	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	n/a	n/a	n/a	n/a	n/a

- Dirt and damp prevention treatment applied.



Textaafoam
creativity in fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl